Red Granular
0-0-60

CHEMICAL COMPOSITION

Component	Symbol	Typical %	Guarantee
Potassium Oxide Equivalent	K_2O	60.8	60% (min.)
Potassium Chloride	KCl	96.3	
Sodium Chloride	NaCl	2.7	
Chloride	Cl-	47.4	
Moisture	H_2O	0.03	

PARTICLE SIZE DISTRIBUTION CUMULATIVE %

Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
5	5	4.00	0 - 10	7
6	6	3.35	20 - 40	30
7	7	2.80	45 - 75	55
8	8	2.36	70 - 95	80
9	10	2.00	90 - 98	95
10	12	1.70	95 - 100	98

PHYSICAL PROPERTIES

Bulk Density (Loose)	Typical
- lb/ft^3	65
- kg/m^3	1040
Angle of Repose	38 Degrees

SIZING CHARACTERISTICS

Parameter	Typical
Size Guide Number (SGN)	293
Uniformity Index (UI)	51

Please refer to the Safety Data Sheet (SDS #: MOS100052) for additional information (www. mosaicco.com)

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values Additional handling, transportation, or improper/extended storage may affect product analyses. Mosaic disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.

Revised 12/15

© Copyright 2015. The Mosaic Company. All Rights Reserved.